

## PLANTOHYD S

**Environmentally friendly hydraulic and lubricating oils based on synthetic ester (HEES), rapidly biodegradable acc. to OECD 301 B > 60 %, awarded with the European Ecolabel (EEL), non water pollutant**

### Description

The products of the PLANTOHYD S-series are environmentally friendly, high-performance lubricating and hydraulic oils based on special synthetic esters. They can be used universally in the temperature range from - 30 °C to + 90 °C and are rapidly biodegradable according to the OECD 301 B test.

The products of the PLANTOHYD S series are awarded with the European Ecolabel EEL. They are based on > 50% sustainable raw materials and are classified as non water pollutant according to the German legislation.

### Application

The products of the PLANTOHYD S-series are synthetic, rapidly biodegradable oils based on sustainable raw materials (> 50%). They are exceptionally suitable for applications in mobile and stationary hydraulic systems, for which a rapidly biodegradable hydraulic oil according to ISO 15380, HEES, is recommended, especially if there is an environmental hazard to the ground, ground water or the surface waters due to leakage (construction, water resources management, agriculture, forestry).

In case of a change to the PLANTOHYD S series products the guidelines for changing fluids according to ISO 15380 must be observed.

### Specifications

The products of the PLANTOHYD S-series fulfill or exceed the requirements according to:

- ISO 15380: HEES
- European Ecolabel (EEL)  
(Euro Margerite)

### Advantages

- Based on sustainable raw materials, > 50%
- Good corrosion protection
- Rapidly biodegradable according to OECD 301 B > 60%
- Multigrade characteristics (rationalisation of varieties)
- Excellent lubricating properties
- Very good viscosity temperature behaviour
- Good low-temperature behaviour
- Highest shear stability
- Natural cleaning capacity
- High ageing stability
- Excellent wear protection
- Good material compatibility
- Non water pollutant according to the German legislation



**EU Ecolabel: PLANTOHYD 15 S: DE/027/154**  
**PLANTOHYD 22 S: DE/027/155**  
**PLANTOHYD 32 S: DE/027/156**  
**PLANTOHYD 46 S: DE/027/157**  
**PLANTOHYD 68 S: DE/027/158**



#### Better for the environment ...

- geringfügige Schädigung von Wasser und Boden bei der Anwendung
- enthält einen großen Anteil von Ausgangsstoffen auf biologischer Basis
- reduced harm for water and soil during use
- contains a large fraction of biobased material

**... better for you.**

## PLANTOHYD S

**Environmentally friendly hydraulic and lubricating oils based on synthetic ester (HEES), rapidly biodegradable acc. to OECD 301 B > 60 %, awarded with the European Ecolabel (EEL), non water pollutant**

### Typical technical data:

Product name		15	22	
Properties	Unit			Test method
ISO VG		15	22	DIN 51519
Kinematic viscosity				DIN EN ISO 3104
at - 20 °C	mm <sup>2</sup> /s	290	475	
at 0 °C	mm <sup>2</sup> /s	80	120	
at 40 °C	mm <sup>2</sup> /s	15	22	
at 100 °C	mm <sup>2</sup> /s	4.1	5.4	
Viscosity index	-	191	197	DIN ISO 2909
Density at 15 °C	kg/m <sup>3</sup>	893	901	DIN 51757
Colour	ASTM	1.0	1.0	DIN ISO 2049
Flash point in open cup acc. to Cleveland	°C	200	200	DIN ISO 2592
Pourpoint	°C	-33	-33	DIN ISO 3016
Neutralisation number	mgKOH/g	0.7	0.7	DIN 51558-1
Scuffing and scoring test, FZG A/8.3/90	failure load stage	10	11	DIN ISO 14635-1
Air release at 50 °C	min	2	2	DIN ISO 9120
Vickers pump test, type V105C				DIN 51389
- weight loss vane	mg	-	pass (< 30)	
- weight loss ring	mg	-	pass (< 120)	
Effect on sealing materials:		60 °C	60 °C	ISO 6072
HNBR, 1008 h:				
- change of Shore A hardness	Shore	- 6.7	- 5.5	
- relative change of volume	%	+ 9.7	+ 8.7	
FKM, 1008 h:				
- change of Shore A hardness	Shore	- 0.7	+ 0.4	
- relative change of volume	%	+ 0.8	+ 0.6	

## PLANTOHYD S

**Environmentally friendly hydraulic and lubricating oils based on synthetic ester (HEES), rapidly biodegradable acc. to OECD 301 B > 60 %, awarded with the European Ecolabel (EEL), non water pollutant**

### Typical technical data:

Product name		32	46	68	
Properties	Unit				Test method
ISO VG		32	46	68	DIN 51519
Kinematic viscosity					DIN EN ISO 3104
at - 20 °C	mm <sup>2</sup> /s	1060	1500	3300	
at 0 °C	mm <sup>2</sup> /s	205	330	590	
at 40 °C	mm <sup>2</sup> /s	32	48	68	
at 100 °C	mm <sup>2</sup> /s	7.1	9.4	12.3	
Viscosity index	-	194	184	181	DIN ISO 2909
Density at 15 °C	kg/m <sup>3</sup>	910	920	924	DIN 51757
Colour	ASTM	1.0	1.0	1.0	DIN ISO 2049
Flash point in open cup acc. to Cleveland	°C	206	300	300	DIN ISO 2592
Pourpoint	°C	- 36	- 45	- 36	DIN ISO 3016
Neutralisation number	mgKOH/g	0.8	1.1	1.1	DIN 51558-1
Scuffing and scoring test, FZG A/8.3/90	failure load stage	12	12	12	DIN ISO 14635-1
Air release at 50 °C	min	3	5	5	DIN ISO 9120
Vickers pump test, type V105C		pass	pass	pass	DIN 51389
- weight loss vane	mg	< 30	< 30	< 30	
- weight loss ring	mg	< 120	< 120	< 120	
Effect on sealing materials:		80 °C	80 °C	100 °C	ISO 6072
HNBR, 1008 h:					
- change of Shore A hardness	Shore	- 4.6	- 3.3	- 3.2	
- relative change of volume	%	+ 7.6	+ 5.8	+ 5.6	
FKM, 1008 h:					ISO 6072
- change of Shore A hardness	Shore	- 0.3	+ 1.0	+ 0.9	
- relative change of volume	%	+ 0.5	+ 0.5	+ 0.4	



## PLANTOHYD S

**Environmentally friendly hydraulic and lubricating oils based on synthetic ester (HEES), rapidly biodegradable acc. to OECD 301 B > 60 %, awarded with the European Ecolabel (EEL), non water pollutant**

The information contained in this product information is based on the experience and know-how of FUCHS SCHMIERSTOFFE GMBH in the development and manufacturing of lubricants and represents the current state-of-the-art. The performance of our products can be influenced by a series of factors, especially the specific use, the method of application, the operational environment, component pre-treatment, possible external contamination, etc. For this reason, universally-valid statements about the function of our products are not possible. The information given in this product information represents general, non-binding guidelines. No warranty expressed or implied is given concerning the properties of the product or its suitability for any given application.

We therefore recommend that you consult a FUCHS SCHMIERSTOFFE GMBH application engineer to discuss application conditions and the performance criteria of the products before the product is used. It is the responsibility of the user to test the functional suitability of the product and to use it with the corresponding care.

Our products undergo continuous improvement. We therefore retain the right to change our product program, the products, and their manufacturing processes as well as all details of our product information sheets at any time and without warning, unless otherwise provided in customer-specific agreements. With the publication of this product information, all previous editions cease to be valid.

Any form of reproduction requires express prior written permission from FUCHS SCHMIERSTOFFE GMBH.

© FUCHS SCHMIERSTOFFE GMBH. All rights reserved.

